# COSWICK HARDWOOD FLOORING | TECHNICAL INFORMATION

Product # 1172-7250

COSWICK Solid Hardwood Floors




**COLLECTION |** HERITAGE
**COLOR |** ANTIQUE PATINA

**Wood species** | Oak
**Grade** | Character
**Constructions** | 3-layer T&G Engineered Flooring
**Size** | 5 x 190 x 600...2100 mm (⅜" x 7 ½" x 2'...7')
**Finish** | Silk finish

## CONSTRUCTION : 3-LAYER T&G ENGINEERED FLOORING

| DIMENSIONS : | |
|---|---|
| Thickness | 15 mm (⅝" ) |
| Width | 190 mm (7 ½) |
| Length | 600 ...2100 mm (2'...7') |
| Average length | |
| Microbevel | 0,5 mm |
| Joint type | tongue and groove (T&G) |




| PACKAGING : | BOX | PALLET |
|---|---|---|
| Content: | 2,26m² | 40 (90,4 m²) |
| Weight | 23 kg | 950 kg |
| H x W x L | 95 x 225 x 2150 mm | 1120 x 905 x 2160 mm |
| Content: | 24,31 sq.ft. | 972,70 sq.ft. |
| Weight | 51 lb | 2100 lb |
| H x W x L | 4" x 10" x 85" | 44" x 36" x 85" |

| DEVIATIONS : | | |
|---|---|---|
| Deviation on Thickness | ± 0,2 mm | EN 13489 ГОСТ 862.3 |
| Deviation on Width | ± 0,2 mm | |
| Height Difference | ≤ 0,2 % of width | |
| Cup | ≤ 0,2 % of plank width | |
| Spring | ≤ 0,1 % of length | EN 13489 |
| Bow | ≤ 0,5 % of length | |

| CHARACTERISTICS : | | |
|---|---|---|
| Fire resistance | Dfl-s1 | EN 14342 |
| Formaldehyde emission class | E1 | |
| Pentachlorophenol content | None | |
| Thermal resistance | 0,095 m²·K/W | |
| Thermal conductivity | 0,158 W/(m·K) | |
| Structural warranty | Lifetime | |

**INSTALLATION :**



Glue down over concrete, plywood or wooden subfloor or nail down over wooden subfloor. Applicable above, on and below ground level. Suitable for installation over radiant heating systems.

**STORAGE AND USAGE :**




— Air humidity 40% – 65%
— Temperature +18 °C – +22 °C

## FINISH : SILK FINISH

| DESCRIPTION : | |
|---|---|
| Type of coating | UV-cured modified polyurethane-acrylate |
| Surface (finish) type | Semi-closed pores, wire brushed |
| Sheen | Silk matte 9-18 GU/85° |
| Finish warranty | - |

| CLASSIFICATION SURFACE CHARACTERISTICS : | | |
|---|---|---|
| Wear resistance | Not rated | EN 438-2 |
| Scratch resistance | Not rated | EN 438 |
| Slip resistance | 50 (SRV dry) | EN 15676 |
| Resistance to chemical agents | Class 5 (Except blue ink) | EN 13442 |
| Repairability | Medium | |

**MAINTENANCE AND CARE CONDITIONS :**

Maintenance of hardwood floors with Silk finish assumes regular (daily if necessary) cleaning from dust and grit using a vacuum, followed by a thorough cleaning with Coswick Hardwood Floor Cleaner or other similar product. Floor surface areas that receive the most traffic and get worn down quicker, such as areas by the front door, hallways, kitchens etc., should be periodically renewed with special Coswick Restorative Oil. This product restores the protective surface film. Frequency of use depends on type of interior and intensity of foot traffic. For residential interiors, restorative cleaning should be done once in 3-5 years; for public and commercial interiors with intense foot traffic, it is recommended to use the product 2-4 times a year.

## GRADE : CHARACTER

| DESCRIPTION : | | DESCRIPTION : | |
|---|---|---|---|
| Sound sapwood | No limit | Bark pocket | No limit (after filling) |
| Colour variation | No limit | Pith | Permitted |
| Knot | Permitted big, filled | Slope of grain | Permitted |
| Crecks | Permitted wide, filled | Medullary ray | Permitted |

**Coswick Ltd.**
2B Kolasa Str., 223034 Zaslavl, Republic of Belarus
Tel.: +375-17-543-2012, Fax: +375-17-543-2020, E-mail: sales@coswick.com
**www.coswick.com**

nwfa National Wood Flooring Association
ECO FRIENDLY No added formaldehyde
СТБ ISO 9001
TP BY CE